



## PRODUCT SPECIFICATION SUPALOX D3803

PRODUCT	High Purity Aluminum Oxide, Al <sub>2</sub> O <sub>3</sub>	PURITY	> 99.98%
---------	--	--------	----------

PARAMETERS	METHOD	SPECIFICATIONS
<b>PHYSICAL PROPERTIES</b>		
Appearance	Visual inspection	White Powder
Crystallinity	XRD	Alpha-alumina
D10	Laser Diffraction	0.3 µm
D50	Laser Diffraction	0.45 µm
D90	Laser Diffraction	0.6 µm
Humidity	2 hrs at 120°C	<1.0 %
Surface Area	N <sub>2</sub> adsorption (BET)	<5 m <sup>2</sup> /g
Tap Density	ASTM B527 - 06	> 0.80 g/cm <sup>3</sup>



<b>CHEMICAL COMPOSITION</b>		
Na	ICP-MS	<60 ppm
Mg	ICP-MS	<10 ppm
Si	ICP-MS	<20 ppm
K	ICP-MS	<5ppm
Ca	ICP-MS	<50 ppm
Fe	ICP-MS	<100 ppm



For technical information, please contact: [info@aemcanada.com](mailto:info@aemcanada.com)

Manufactured with virtually zero CO<sub>2</sub> emission in CANADA