

PRODUCT SPECIFICATION SUPALOX O4041

PRODUCT	High Purity Alumina Slurry, Al ₂ O ₃	PURITY	> 99.99%
---------	--	--------	----------

PARAMETERS	METHOD	SPECIFICATIONS
PHYSICAL PROPERTIES		
Appearance	Visual inspection	White Slurry
Al ₂ O ₃ Crystallinity	XRD	Alpha-Alumina
Solid PSD	D10	Laser Diffraction
	D50	Laser Diffraction
	D90	Laser Diffraction
Solid content*	---	70 %
Slurry Density	---	2.1 g/cm ³
pH*	---	4-6
Shelf Life	10-30 °C	6 Months


* Can be tailored according request

CHEMICAL COMPOSITION		
Na	ICP-MS	<40 ppm
Mg	ICP-MS	<5 ppm
Si	ICP-MS	<30 ppm
K	ICP-MS	<3 ppm
Ca	ICP-MS	<10 ppm
Fe	ICP-MS	<10 ppm



SUPALOX O4041 is a ball-mill deagglomerated product and formulated from our High Purity Alumina powders. The composition has been developed to provide a suspension of alumina in a nontoxic base.

We advise to use these products within 6 months after reception and store it in standard conditions ideally under agitation.



For technical information, please contact: info@aemcanada.com

Manufactured with virtually zero CO₂ emission in CANADA 