

## PRODUCT SPECIFICATION SUPALOX O4041

PRODUCT	High Purity Alumina Slurry, Al <sub>2</sub> O <sub>3</sub>	PURITY	> 99.99%
---------	--	--------	----------


PARAMETERS	METHOD	SPECIFICATIONS
<b>PHYSICAL PROPERTIES</b>		
Appearance	Visual inspection	White Slurry
Al <sub>2</sub> O <sub>3</sub> Crystallinity	XRD	Alpha-Alumina
Solid PSD	D10	Laser Diffraction
	D50	Laser Diffraction
	D90	Laser Diffraction
Solid content*	---	70 %
Slurry Density	---	2.1 g/cm <sup>3</sup>
pH*	---	4-6
Shelf Life	Storage at 5-30 °C	6 Months

\* Can be tailored according request

<b>CHEMICAL COMPOSITION</b>		
Na	ICP-MS	<40 ppm
Mg	ICP-MS	<5 ppm
Si	ICP-MS	<30 ppm
K	ICP-MS	<3 ppm
Ca	ICP-MS	<10 ppm
Fe	ICP-MS	<10 ppm



SUPALOX O4041 is a ball-mill deagglomerated product and formulated from our High Purity Alumina powders. The composition has been developed to provide a suspension of alumina in a nontoxic base.



For technical information, please contact: [info@aemcanada.com](mailto:info@aemcanada.com)

Manufactured with virtually zero CO<sub>2</sub> emission in CANADA 