

PRODUCT SPECIFICATION SUPALOX O3041

PRODUCT	High Purity Alumina Slurry, Al ₂ O ₃	PURITY	> 99.9%
---------	--	--------	---------


PARAMETERS	METHOD	SPECIFICATIONS
PHYSICAL PROPERTIES		
Appearance	Visual inspection	White Slurry
Al ₂ O ₃ Crystallinity	XRD	Alpha-Alumina
Solid PSD	D10	Laser Diffraction
	D50	Laser Diffraction
	D90	Laser Diffraction
Solid content*	---	70 %
Slurry Density	---	2.1 g/cm ³
pH*	---	4-5
Shelf Life	Storage at 5-30 °C	6 Months

* Can be tailored according request

CHEMICAL COMPOSITION		
Na	ICP-MS	<500 ppm
Mg	ICP-MS	<10 ppm
Si	ICP-MS	<20 ppm
K	ICP-MS	<5 ppm
Ca	ICP-MS	<50 ppm
Fe	ICP-MS	<100 ppm



SUPALOX O4041 is a ball-mill deagglomerated product and formulated from our High Purity Alumina powders. The composition has been developed to provide a suspension of alumina in a nontoxic base.



For technical information, please contact: info@aemcanada.com

Manufactured with virtually zero CO₂ emission in CANADA 