

Groupe AEM Canada 7220 Rue Frederick-Banting Saint-Laurent, Quebec Canada H4S 2A1 www.aemcanada.com

## PRODUCT SPECIFICATION SUPALOX ON11 (70)


PRODUCT	High Purity Alumina Slurry, Al <sub>2</sub> O <sub>3</sub>	PURITY	> 99.99%
---------	--	--------	----------

PARAMETERS		METHOD	SPECIFICATIONS			
TYPICAL PHYSICAL PROPERTIES						
Appearance		Visual inspection	White Slurry			
Al <sub>2</sub> O <sub>3</sub> Crystallinity		XRD	Alpha-Alumina			
	D10	Laser Diffraction	0.3 μm			
Solid PSD	D50	Laser Diffraction	0.5 μm			
	D90	Laser Diffraction	1.8 μm			
Solid content			70 %			
Slurry Density			2.1 g/cm <sup>3</sup>			
рН			4-6			
Shelf Life		Storage at 5-30 °C	6 Months			

TYPICAL CHEMICAL COMPOSITION					
Na	ICP-MS	<40 ppm			
Mg	ICP-MS	<5 ppm			
Si	ICP-MS	<30 ppm			
K	ICP-MS	<3 ppm			
Са	ICP-MS	<10 ppm			
Fe	ICP-MS	<10 ppm			



SUPALOX ON11 (70) is a ball-mill deagglomerated product and formulated from our High Purity Alumina powders. The composition has been developed to provide a suspension of alumina in a nontoxic base.



For technical information, please contact: <a href="mailto:info@aemcanada.com">info@aemcanada.com</a>